

Justseal



Description

- Justseal is a high performance, low-middle modulus, one part acetoxy curing silicone sealant
- The product has capable of repeated extension and compression during service with excellent resistance to aging, shrinkage, cracking and discoloration
- It offers long term durability in a range of general sealing and general glazing applications
- Cures to a strong, flexible seal capable of withstanding movement in and around the joint
- Excellent weather resistance & tooling properties for professional use
- Non-slumping, can be used in vertical and overhead joints
- Excellent un-primed adhesion to a wide variety of construction materials and building components

Range

Product Code	Size	Colour	Unit Qty	Carton Qty
238-502-300	290ml	Clear	1	24
238-502-305	290ml	White	1	24

Olympic Fixing Products Ltd

Units 1-3 Venture Court, Metcalf Drive
Altham, Accrington
Lancashire BB5 5WH

Tel: +44 (0)1282 778923 (5 lines)
Fax: +44 (0)1282 779119

Sales Enquiries: accrington@olympicfixings.co.uk
General Enquiries: accrington@olympicfixings.co.uk
New Account Requests: tc@olympicfixings.co.uk

Company Registration No: 02367267 VAT Registration No: GB 572277230

Olympic Fixings Ireland Ltd

Unit 3, Greenway Industrial Estate
Conlig, Co. Down
BT23 7SU

Tel: +44 (0)2891 453724 (4 lines)
Fax: +44 (0)2891 465893

Sales Enquiries: bangor@olympicfixingsireland.com

www.olympicfixings.com

Company Registration No: 02666419 VAT Registration No: GB 598063891

Registered Office:

Units 1-3 Venture Court, Metcalf Drive, Altham,
Accrington, Lancashire BB5 5WH

Technical Features

Items	C*a/T*b/S*c/O*d	Unit	Typical Value	Requirement	Test Std	Eqv. Std
Appearance		/	/	Thixotropic Paste	Q/JL-00-T001	
Density		g/cm ³	0.98	0.98±0.50	GB/T 13477.2	
Tack free	///Finger	min	6	≤15	GB/T 13477.5	ASTM D2377:2000
Sagging		mm	0	≤1	GB/T 13477.6	ISO 7390:1987
Hardness, Shore A	7d///	/	22	10~30	GB/T 531.1	ISO 7619-1:2004
Curing Depth	24h///	mm	3.0	≥3.0	GB/T 32369	
Curing Depth	7d///	mm	6.0	≥6.0	GB/T 32369	
Elongation at break	7d///	%	650	≥400	GB/T 528	ISO 37:2005
Tensile Strength	7d///	MPa	0.98	≥0.8	GB/T 528	ISO 37:2005

Notes: *a. Conditioning, specimen is conditioned under (23±2) °C, (50±5)% relative humidity if not specified;
*b. Testing Condition, specimen is tested at (23±2) °C, (50±5)% relative humidity if not specified;
*c. Substrate
*d. Others need to be specified.
The above data is intended to provide guidance for use and should not be used to write product specifications

Storage

- 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and 27°C with humidity between 30% and 70%
- Optimal storage is at the lower half of this temperature range and humidity range
- To prevent contamination of unused product, do not return any material to its original container.

Olympic Fixing Products Ltd
Units 1-3 Venture Court, Metcalf Drive
Altham, Accrington
Lancashire BB5 5WH

Tel: +44 (0)1282 778923 (5 lines)
Fax: +44 (0)1282 779119

Sales Enquiries: accrington@olympicfixings.co.uk
General Enquiries: accrington@olympicfixings.co.uk
New Account Requests: tc@olympicfixings.co.uk

Olympic Fixings Ireland Ltd
Unit 3, Greenway Industrial Estate
Conlig, Co. Down
BT23 7SU

Tel: +44 (0)2891 453724 (4 lines)
Fax: +44 (0)2891 465893

Sales Enquiries: bangor@olympicfixingsireland.com

www.olympicfixings.com

Company Registration No: 02666419 VAT Registration No: GB 598063891

Registered Office:
Units 1-3 Venture Court, Metcalf Drive, Altham,
Accrington, Lancashire BB5 5WH

Company Registration No: 02367267 VAT Registration No: GB 572277230